



长纤（厦门）新材料科技有限公司

Xiamen LFT Composite Plastic Co.,Ltd

Technical Data Sheet

LFT-G® RTPU-NA-LGF40

Product Name	● LFT-G® RTPU-NA-LGF40
Resin Description	● Rigid Thermoplastic Polyurethane
Fiber Type	● Long Glass Fiber
Fiber Content	● 40%
Color	● Natural, and custom colors
Processed Method	● Injection molding

Physical	Typical Characteristic	Testing Standard
比重 Specific Gravity	1.51 g/cm ³	ASTM D-792
成型收缩率 Molding Shrinkage	0.10~ 0.20 %	ASTM D-955 (1/8 in (3.2 mm)section)

Mechanical	Typical Characteristic	Testing Standard
拉伸强度 Tensile Strength	205 MPa	ASTM D-638
拉伸模量 Tensile Modulus	10900 MPa	ASTM D-638
拉伸伸长率 Tensile Elongation	1.8 - 2.3 %	ASTM D-638
弯曲强度 Flexural Strength	308 MPa	ASTM D-790
弯曲模量 Flexural Modulus	9998 MPa	ASTM D-790
悬臂梁缺口冲击强度 Notched Izod Impact	360 J/m	ASTM D-256
未切口冲击强度 Un-Notched Izod Impact	1502 J/m	ASTM D-4812

LFT-G® RTPU-NA-LGF40

Thermal	Typical Characteristic	Testing Standard
热变形温度 Deflection Temperature @ 264 psi (1820 kPa)	240 ° C	ASTM D-648

Flammability	Typical Characteristic	Testing Standard
阻燃性 Flame Retardant	HB @ 1.5 mm	ASTM D-635

Injection	Typical Characteristic
注塑压力 Injection Pressure	70 ~105 MPa
熔体温度 Melt Temperature	220~ 260 ° C
模具温度 Mould temperature	45~70 ° C
干燥 Pre-drying	3~5 hrs @ 80~100 ° C
水分含量 Moisture Content	0.01 %

Processing Notes

Molding guidelines and processing conditions for LFT-G® long fiber composite pellets are available in our Material Processing Guide. Please contact our technical support team if you require additional information regarding processing a particular product or guidance resolving problems.

Values included in this Property Data Sheet are based on limited laboratory test specimens. These values are typical values and are not meant to be used for setting maximum or minimum values for specification purposes. Any determination of the suitability of the materials shown in this property data sheet for use by the end user is the sole responsibility of the user, who must assure himself that the material as subsequently processed meets the need of his particular product or use. To the best of our knowledge the information in this publication is accurate and reliable, LFT-G® does not assume any liability whatsoever for the accuracy of this information.

Web : www.lfirt-plastic.com
Email : candyhu@lfirtplastic.com
Tel : 0086 186 5906 9962
Availability : Global